

**AMENDMENTS**Amendments to the Claims

Please amend the claims according to the following listing of the claims.

Listing of the claims

1-23. (canceled)

24. (currently amended) A laminated sheet or film comprising the following (co)extruded layers:  
a substrate layer comprising based on the sum of the amounts of the following components A, B and C and, if used, D, which totals 100% by weight -

1 - 99% by weight component A, which is of a graft copolymer of

55 - 80% by weight of a particulate graft base A1 comprising the following monomers:

95-99.9% by weight of at least one C<sub>1-8</sub>-alkyl ester of acrylic acid as component A11;

0.1-5.0% by weight of at least one polyfunctional crosslinking monomer as component A12;

20 - 45% by weight of a graft A2 comprising the following monomers, based on A2:

60 - 85% by weight of units of styrene, a substituted styrene or a (meth)acrylate, or mixtures thereof, as component A21 and

15-35% by weight of units of acrylonitrile or methacrylonitrile as component A22;

the graft A2 comprising at least one graft shell and the graft copolymer having a mean particle size of 50 - 1000 nm;

1 - 99% by weight of component B, which is a copolymer of

60 - 85% by weight of units of styrene, a substituted styrene or a (meth)acrylate, or mixtures thereof, as component B1, and

15 - 40% by weight of acrylonitrile or methacrylonitrile as component B2;

10 - 80% by weight of a ground or granulated component C, which ~~is~~ consists of a polycarbonate; and

0 - 50% by weight of component D, which is a fibrous or particulate filler or mixtures thereof;

a transparent top layer of polymethyl methacrylate and optionally,

between the top layer and the substrate layer,

~~an~~ a (co)extruded interlayer of impact-modified polymethyl methacrylate, polycarbonate or a molding composition of said substrate layer without polycarbonate, ~~if said substrate layer contains polycarbonate.~~

25. (canceled)

26. (previously presented) A laminated sheet or film as defined in claim 24, having an overall thickness of from 100  $\mu\text{m}$  to 10 mm.

27-29. (canceled)

30. (previously presented) A laminated sheet or film as defined in claim 24, wherein the ratio of the MFI values of the individual components of the laminated sheet or film is not more than 3:1.

31. (previously presented) A molding comprising a shaped laminated sheet as defined in claim 24.
- 32-33. (canceled)
34. (previously presented) A molding as defined in claim 31 in the form of an automotive exterior bodywork component.
- 35-40. (canceled)
41. (currently amended) A laminated sheet or film comprising the following (co)extruded layers:  
a substrate layer comprising based on the sum of the amounts of the following components A, B and C and, if used, D, which totals 100% by weight -  
1 - 99% by weight component A, which is of a graft copolymer of  
55 - 80% by weight of a particulate graft base A1 comprising the following monomers:  
95 - 99.9% by weight of at least one C<sub>1-8</sub>-alkyl ester of acrylic acid as component A11;  
0.1 - 5.0% by weight of at least one polyfunctional crosslinking monomer as component A12;  
20 - 45% by weight of a graft A2 comprising the following monomers, based on A2:  
60 - 85% by weight of units of styrene, a substituted styrene or a (meth)acrylate, or mixtures thereof, as component A21 and  
15 - 35% by weight of units of acrylonitrile or

methacrylonitrile as component A22;  
the graft A2 comprising at least one graft shell  
and the graft copolymer having a mean particle  
size of 50 - 1000 nm;

1 - 99% by weight of component B, which is a copolymer  
of

60 - 85% by weight of units of styrene, a  
substituted styrene or a (meth)acrylate, or  
mixtures thereof, as component B1, and  
15 - 40% by weight of acrylonitrile or  
methacrylonitrile as component B2;

10 - 80% by weight of a ground or granulated component  
C, which ~~is~~ consists of a polycarbonate; and

0 - 50% by weight of component D, which is a fibrous  
or particulate filler or mixtures thereof;

a transparent layer of polymethyl methacrylate and a  
transport protection film applied to the outside of  
said layer of polymethyl methacrylate.

42. (canceled)

43. (currently amended) A laminated sheet or film  
comprising the following (co)extruded layers:  
a substrate layer comprising based on the sum of the  
amounts of the following components A, B and C and, if  
used, D, which totals 100% by weight -

1 - 99% by weight component A, which is of a graft  
copolymer of

55 - 80% by weight of a particulate graft base A1  
comprising the following monomers:

95 - 99.9% by weight of at least one C<sub>1-8</sub>-alkyl  
ester of acrylic acid as component A11;

0.1 - 5.0% by weight of at least one polyfunctional crosslinking monomer as component A12;

20 - 45% by weight of a graft A2 comprising the following monomers, based on A2:

60 - 85% by weight of units of styrene, a substituted styrene or a (meth)acrylate, or mixtures thereof, as component A21 and

15 - 35% by weight of units of acrylonitrile or methacrylonitrile as component A22;

the graft A2 comprising at least one graft shell and the graft copolymer having a mean particle size of 50 - 1000 nm;

1 - 99% by weight of component B, which is a copolymer of

60 - 85% by weight of units of styrene, a substituted styrene or a (meth)acrylate, or mixtures thereof, as component B1, and

15 - 40% by weight of acrylonitrile or methacrylonitrile as component B2;

10 - 80% by weight of a ground or granulated component C, ~~which-is~~ consists of a polycarbonate; and

0 - 50% by weight of component D, which is a fibrous or particulate filler or mixtures thereof;

a transparent top layer of styrene-acrylonitrile copolymer,

and optionally

~~an~~ a (co)extruded interlayer of a styrene-acrylonitrile copolymer.